

AMTRADE CORPORATION

POLYESTER INDUSTRIAL YARN AA HIGH TENACITY

DECITEX (dtex)	1111	2222	3333
DENIER	1000	2000	3000
FILAMENT	192	384	384
TENACITY (cN/dtex)	8.0	8.0	8.0
ELONGATION (%)	13-15	13-15	13-15
DRY SHRINK (%) AT 177 °C, 10 Min. 0.05cN/dtex	7.5 (+/- 1.5%)	7.5 (+/- 1.5%)	7.5 (+/- 1.5%)

PACKAGING SPECIFICATION - ALL DENIERS

Packages - Net Wt. (Lbs.)	22
Outside Diameter(in.)	8.5
Inside Diameter(in.)	2.875
Length of Tube(in.)	13
Length of Stroke(in.)	12
Packages/carton	
Packages/pallet	