

AMTRADE CORPORATION

NYLON 66 INDUSTRIAL YARN

DENIER	840	1260	1680	1890
FILAMENT	140	208	280	312
LINEAR DENSITY (DTEX)	940 ± 17	1400 ± 23	1870 ± 33	2100 ± 39
BREAKING STRENGTH (N)	≥78.0	≥117.20	≥156.40	≥176.50
ELONGATION AT BREAK (%)	19± 3	19± 3	19± 3	19± 3
ELONGATION AT LOAD (%)	12 ± 1.5 (44.1 N) (4.5 Kg)	12 ± 1.5 (66.6N) (6.8 Kg)	12 ± 1.5 (88.2 N) (9.0 Kg)	12 ± 1.5 (100 N) (10.2 Kg)
HEAT STABILITY (%) (Dry Air at 180°C 4 Hrs.)	≥ 90	≥ 90	≥ 90	≥ 90
SHRINKAGE IN BOILING WATER (%) (30 MIN.)	7 ± 2	7 ± 2	7 ± 2	7 ± 2

PACKAGE INFORMATION:

1. Weight: 22 Lbs.
2. Traverse length: 10.16 In.
3. Outside Diameter: 9.8 In.
4. Internal Diameter: 2.95 In.
5. Tube Length: 11.4 In.